

Characteristics:

White, unfinished surface, cellulose with wet strength resin

Physical Property	Standard Units		Metric Units	
Basis Weight	lbs/1389ft ²	20.0	gsm	70.2
Basis Weight	oz/yd ²	2.07		
Thickness	mils	6.3	mm	0.1600
Rapidity			mls/min	65.0
Frazier Permeability	cfm/ft ²	1.5	L/m ² /sec	12.0
Tensile Strength MDT Dry	lb/in	14.0	N/m	2452
Tensile Strength CDT	lb/in		N/m	
Retention	micron	3.0		
Wet Burst	in	120.0	cm	304.8

Micron ratings are based on an Ahlstrom test method where 98% of a particulate size is removed during gravitational filtration. Micron rating values vary between industries and manufacturers depending on the test procedure.